



74 Kent Street
Brooklyn, New York 11222-1517

Phone (718) 383-5080
Fax (718) 383-7445
E-mail: dllabs@aol.com

Accredited by National Voluntary Laboratory Accreditation Program - Lab Code 100252
ISO / IEC 17025 and relevant requirements of ISO 9002

March 5, 1999

Superior Products International
P.O. Box 1930
Independence, MO 64055

Att: Mr. J. E. Pritchett
President

Re: DL-12111A-16

OBJECTIVE

To test a coating for compliance to the requirements for mildew resistance as outlined in Par. 10.12 of ASTM E-1795, "Standard Specification for Non-Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Buildings", Type III, Either Exterior or Interior Use.

PRODUCT TESTED

Rust Grip

TEST PROCEDURES

The coating was applied in two coats, 6 mils wet per coat with four hours dry between coats and allowed to cure twenty-one days at ambient conditions before testing in accordance with procedures outlined in ASTM E-1795.

TEST RESULTS

The sample of Rust Grip exhibited the following mildew resistance property.

<u>Property</u>	<u>Requirement</u>	<u>Result</u>
Mildew Resistance	8 minimum Very slight growth	10 No growth

CONCLUSION

The sample of Rust Grip conforms to the requirements for mildew resistance as outlined in ASTM E-1795, Standard Specification for Non-Reinforced Liquid Coatings Encapsulation Products for Leaded Paint in Buildings, Type III, Either Exterior or Interior Use.

DL Labs, Inc.

A handwritten signature in black ink, appearing to read 'Mario Lazaro, Jr.'.

Mario Lazaro, Jr.
Assistant Technical Director